



DESCRIPTION

Avery Dennison® Y5660W is a pre-combined diaper tape system, incorporating soft hook elements and a Y-bond between fastening and release tape. The mechanical closure provides to the end-user additional security and ease-of-use over the traditional tapes. The product is supplied as a single roll.

CONSTRUCTION


white soft non-woven tape: 62mm
superhook elements: 13mm
white polypropylene tape: 21mm
folding position: 20mm

产品描述

Avery Dennison® Y5660W是一种由预复合的柔软魔术 搭扣及由固定胶带(FT)与离型胶带(RT)形成的Y型结构 组合而成的用于可抛 弃纸尿裤的侧腰贴。相对于传统的 胶带, 魔术搭扣更加安全且方便最终用户使用.

结构组成

白色柔软的无纺布胶带: **62mm** 超级魔术搭扣 **13mm** 白色聚丙烯薄膜胶带 **21mm** 折叠位置 **20mm**



FEATURES & BENEFITS

- Y-bond providing strongest possible bond with diaper chassis
- Nonwoven-like fastening tape increasing the softness of the closure system
- Possible folding issues solved due to Y-bond construction
- Aggressive hook element used for better peel performance into multiple loop landing zones
- Excellent adhesion of release tape to a wide variety of polyethylene's and polypropylene nonwoven substrates
- Product supplied as a single roll

产品的特点与优点

- Y型结构可与尿裤本身进行极佳的粘接
- 无纺布的固定胶带使整个侧腰贴更加柔软
- Y型预复合结构使在线折边更加容易
- 新型的超级魔术搭扣可与各种类型的Loop配合,提供更 佳的剥离性能
- 固定胶带粘接剂提供安全理想的粘接效果,适用于聚乙烯薄膜和无纺布等基材。离型胶带粘接剂则能与聚乙烯(PE)、聚丙烯(PP)无纺材料很好的粘接在一起。

STANDARD FORMAT

Roll width/ 卷宽: 62mm Roll length/卷长: 280 m

产品规格

Inside diameter of the core/内径: 76 mm Outside diameter of the roll/外径: 450 mm

^{*} All above dimensions are typical values, only for reference.

PHYSICAL PROPERTIES 物理性能	TYPICAL VALUES 典型数值	UNITS 单位	TEST METHODS 测试方法
Precombined tape/预复合胶带:			
Roll unwind release/解卷离型力	low		
Fastening tape/固定胶带: 90° Peel Hooks/Avery Loops(peak)	200	N/m	T04/612
180° peel Hook/Tape			
(180° 剥离力魔术搭扣 vs 胶带)	270	N/m	T04/605
Fastening tape – permanent part/固定胶带 - 90° peel on PE film*剥离力(PE 膜*)	-固定部分 250	N/m	T04/100
Release tape/离型胶带:			
90° Peel on PE Film*/剥离力(PE 膜*)	260	N/m	T04/100

*Avery Dennison® Standard Poly film.

STORAGE and SHELF LIFE

One year when stored in original packaging at 21°C (70° F), 50% relative humidity and out of direct sunlight.

IMPORTANT

Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine prior to use the suitability of this material for their specific purposes. All Avery Dennison materials described herein are sold subject to Avery Dennison's Conditions of Sales, a copy of which is available upon request..

产品的储存及有效期

在 21℃(70℃),相对湿度 50%,避免被阳光直射条件 储存。在上述条件下未开封的本产品可存放一年。

说明

上述性能信息是基于我们认为可靠的测试,所得出的 数值是典型值,在不同的应用条件下会有变化。所有 数值仅作为信息参考,并不构成保证或担保。任何买 方应在使用前已独立确定该产品对其具体用途是否适 用。此处描述的所有艾利丹尼森材料受限于艾利丹尼 森的销售条款,如有要求我们可提供副本。

Please refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2015 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance Tapes

Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335 Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379 Fax: +1 888-358-4469